

In Dublin were totally refurbished

in December 2007.

REFERENCES

Ref: IE-CI-Fountains – EN 09/10/2008

1/2

www.zinga.eu

FOUNTAIN IN PEOPLE'S PARK – DUBLIN – IRELAND

The castings of these fountains were done in Glasgow, Scotland circa 1850, so they have a wonderful history. The last refurbishment was done just after World War II. Picture left, one of the 2 blue-white These cast-iron fountains in the People's Park

(picture taken in April 2007)



Blast cleaning to remove the old paint. (picture taken on 18-12-2007)





Detail of the fully blasted fountain

The cast-iron has been totally blasted, then all small holes, corners and edges were spot touched up with ZINGA with a short brush, then the whole structure was protected with ZINGA and sprayed with the additional intermediate and topcoats.



REFERENCES

Ref: IE-CI-Fountains – EN 09/10/2008

www.zinga.eu



(picture left)
View of the first fountain, competely finished.
Picture taken on 11 May 2008

You see the white angels (coating brand unknown) as well as the green chlorinated rubber final coat on the other parts.



(picture right)

An inspection was held in August 2019, almost 12 years after application.

The white topcoat (unknown brand) on the angels has totally disappeared.

The green chlorinated rubber coat has also disappeared after almost 12 years.

But the remaining coating, with ZINGA and ZINGALUFER is still intact and in perfect condition, and no corrosion is visible.

System: SA 2,5

 $\begin{array}{ccc} \text{ZINGA} & \text{1 x 60 } \mu\text{m DFT} \\ \text{Zingalufer} & \text{1 x 80 } \mu\text{m DFT} \\ \text{Chlorinated rubber enamel} & \text{1 x 60 } \mu\text{m DFT} \\ \end{array}$