

Coating the Gates at Blenheim Palace

Coated in August 2002



Coating system: Total film-build = 320µm DFT

Zinga: 1 x 80µm DFT

Alufer: 2 x 40µm DFT + 1 x 80 µm DFT

Vinyl: 1 x 80 µm DFT